

# Lithium Niobate Wafers-SAW

## Lithium Niobate (LiNbO<sub>3</sub>) Wafers ..... SAW Grade


Vin Karola offers a variety of Lithium Niobate (LiNbO<sub>3</sub>) single crystal wafers suitable for use in the SAW (Surface Acoustic Wave) devices. This is a non-optical application, and less demanding in terms of impurities, and crystalline perfection.

- ✚ SAW Grade LiNbO<sub>3</sub> wafers
- ✚ Y-axis, 128° RY and 64° RY Orientations
- ✚ 100mm dia x 0.5mm thick
- ✚ One side polished



### Features:

Standard Diameter	100mm
Standard Thickness	0.5mm
Warp	< 50 microns (free state)
TTV (Total Thickness Variation)	< 25 microns
Surface Finish	<u>Side 1:</u> Polish No pits or scratches within the working area (wafer dia less 1mm around the edge). Inspected with unaided eye using reflected light.  <u>Side 2:</u> Ground (Ra: 0.5 – 0.7 micron)
Wafer Flat	<u>Primary Flat</u> (perpendicular to X-axis) <u>Secondary Flat</u> (90° clockwise from the primary flat when viewing the polished face)
Edge Chips	< 0.5mm in depth, and < 1mm in length
Orientations Available	<b>Y-axis, 128° RY, and 64° RY</b>



VIN KAROLA INSTRUMENTS

P.O. Box 922273  
Norcross, GA 30010-2273  
Tel: 770/409-1499  
Fax: 770/447-8045  
e-mail: info@vinkarola.com